



## SPECIFICATIONS FOR BITUMEN 60/70

	SPECIFICATION	TEST METHOD
Specific Gravity @ 25/25 C	1.01-1.06	D-70
Penetration @ 25 C	60/70	D-5
Softening Point C	49/56	D-36
Ductility @ 25 C	100 min	D-113
Loss on Heating (wt) %	0.2 max	D-6
Drop in penetration after heating %	20 max	D-6 & D-5
Flash Point C	250 min	D-92
Solubility in CS <sub>2</sub> (wt) %	99.5 min	D-4
Spot Test	Negative	A.A.S.H.O.T.102

## АПЕК ПАСИФИК ЭНЕРЖИ КОРПОРАЙШН

**APEC Address:**

Bld.3'3 Kostina ST. 603000 Nighnovgorod-Russia

**TEL:**

+79101044964

+79524578369

**Fax:** +603-21815007

**Email:**

[Info@apecholding.com](mailto:Info@apecholding.com)